

REPORT OF TEST



SGS U.S. Testing Company Inc.

291 Fairfield Avenue • Fairfield, NJ 07004-3833 • Tel: 201-575-5252 • Fax: 201-244-1823

Report Number: 203609-01
Date: 06/27/97
Page: 1 of 2

Client: Inpro Corporation
 S. 80W. 18766 Apollo Drive/PO Box 406
 Muskego, WI 53150

Subject: Samples submitted and identified by the client as: Rigid Vinyl Material (PVC).

Sample Description: 2"x2" white squares.

Project: Fungal and Bacterial Resistance Testing

Test Dates: 05/29/97 - 06/26/97

Procedure: A. ASTM G-21

The testing was conducted in accordance with the procedures outlined in ASTM G-21-90, "Determining Resistance of Synthetic Polymeric Materials to Fungi".

The samples were placed on a mineral salts medium and sprayed with a combined inoculum of the following spore suspensions.

	<u>ATCC #</u>
<u>Aspergillus niger</u>	9642
<u>Penicillium funiculosum</u>	9644
<u>Chaetomium globosum</u>	6205
<u>Gliocladium virens</u>	9645
<u>Aureobasidium pullulans</u>	9348

After inoculation, samples and controls were placed in a "tropical test chamber" and incubated at a temperature of 30 ± 1°C relative humidity greater than 85%.

The total incubation period was 21 days.

Prepared by:


SIGNED FOR THE COMPANY BY:

Miguel Lijo
 Laboratory Technician

D. Keith Goins, Ph.D.
 Manager, Microbiology

ANALYTICAL SERVICES • PERFORMANCE TESTING • STANDARDS EVALUATION • CERTIFICATION SERVICES
 SGS U.S. TESTING COMPANY INC. REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANYONE RELYING ON SUCH REPORTS SHOULD UNDERSTAND ALL OF THE DETAILS OF THE ENGAGEMENT. REPORTS REFLECT RESULTS ONLY OF THE STANDARDS OR PROCEDURES IDENTIFIED TO THE TESTS CONDUCTED AND ARE LIMITED TO THE SAMPLES TESTED. TEST RESULTS MAY NOT BE INDICATIVE OF THE QUALITIES OF THE LOT FROM WHICH THE SAMPLE WAS TAKEN. SGS U.S. TESTING COMPANY INC. HAS NOT CONDUCTED ANY QUALITY CONTROL PROGRAM FOR THE CLIENT. NEITHER THE NAME, SEALS, MARKS NOR INSIGNIA OF SGS U.S. TESTING COMPANY INC. MAY BE USED IN ANY ADVERTISING OR PROMOTIONAL MATERIALS WITHOUT THE PRIOR WRITTEN APPROVAL OF SGS U.S. TESTING COMPANY INC. THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL WITHOUT THE WRITTEN PERMISSION OF THE SGS U.S. TESTING COMPANY INC. SAMPLES NOT DESTROYED IN TESTING ARE DISPOSED OF AFTER 30 DAYS.

REPORT OF TEST



Client: Inpro Corporation

Report Number: 203669-01

Date: 06/27/97

Page: 2 of 2

B. ASTM G-22

The testing was conducted in accordance with the procedures outlined in ASTM G-22, "Determining Resistance of Synthetic Polymeric Materials to Bacteria".

The samples were placed on a mineral salts medium and inoculated with the test organisms *Pseudomonas aeruginosa*, ATCC #13388, *E. Coli* ATCC #8739 and *Staphylococcus aureus* 6538. The test sample and control were then incubated 21 days at 35°C and 85% Relative Humidity.

* *E. Coli* and *Staphylococcus aureus* were tested at the client's request.

Results:

A. ASTM G-21

<u>Sample</u>	<u>Evaluation of Fungal Growth</u>
Rigid Vinyl Material (PVC)	0
Environmental Controls (paper, cork, cotton, leather)	3,4
Viability Control	4

<u>*ASTM Rating</u>	<u>Observed Growth on Specimens</u>
0	None
1	Traces of Growth (less than 10%)
2	Light Growth (10-30%)
3	Medium Growth (30-60%)
4	Heavy Growth (60% to complete coverage)

B. ASTM G-22

<u>Sample</u>	<u>Evaluation of Bacterial Growth</u>
Rigid Vinyl Material (PVC)	0
Viability Control	Heavy Growth

Conclusion: The submitted samples of Rigid Vinyl Material (PVC) did not support fungal or bacterial growth, when tested as specified.